ISO-5.10-FR15.02

## Ballistic Resistance – Test Report

Kratos Glass LLC.

Attention: Fadi Michael

Client: Dubai Investment Park 2

United Arab Emirates

10 February 2017 Report date:

000006895

Test procedure and supporting documentation:

Per Customer Instructions

Sample receipt, identification information,

and disposition:

Job number:

The sample(s) were received on 8 February 2017. Sample item identification and description details are provided on the attached data record(s). The test sample(s) were inspected prior to testing and no anomalies were discovered. Sample(s) will be

returned, discarded, or held, per customer instructions.

Test date(s) and location:

Testing commenced on 9 February 2017, at the H.P. White Laboratory, Inc. facilities located at 3114 Scarboro Road, Street, Maryland. Testing concluded on 9 February

Report prepared by:

Ashley Gowland, Customer Operations Coordinator

Report reviewed by:

Wesley Mason, Manager of Technical Operations - Hard Armor

Revision number and date:

Test data transmittal method and storage

location:

Disclaimer:

This test report and test data were transmitted via email in a manner compliant with ISO 17025 requirements. Permanent electronic and hardcopy files are maintained in accordance with HPWLI data storage policy on data storage systems, filed by job number.

Testing was performed on sample(s) provided by the client. H.P. White Laboratory, Inc. holds no responsibility for sample selection methods. This report is based on data obtained from testing only the sample(s) submitted, and should NOT be interpreted as an endorsement by H.P. White Laboratory, Inc. of the continuing quality or performance of any other items of the same, or similar, design. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST, or any agency of the Federal Government. This testing was performed by H.P. White Laboratory, Inc. to client specification, and the test results are the property of the client, who holds all rights of reproduction or publication of this report and related test data.

These items are controlled by the U.S. government and authorized for export only to the country of ultimate destination for use by the ultimate consignee or end-user(s) herein identified. They may not be resold, transferred, or otherwise disposed of, to any other country or to any person other than the authorized ultimate consignee or enduser(s), either in their original form or after being incorporated into other items, without first obtaining approval from the U.S. government or as otherwise authorized

**Destination control** statement:

by U.S. law and regulations.



## H.P. White Laboratory, Inc.

BALLISTIC RESISTANCE TEST

Client: 6075: Kratos Glass, LLC

Job No.: 000006895

Test Date: 2/9/17

## **TEST PANEL**

Manufacturer: Kratos Glass, LLC

Size: 19.750 X 19.750 in.

Thicknesses: 1.575, 1.576, 1.580, 1.586 in.

Avg. Thick.: 1.579 in.

Description: 40mm Laminated Transparency

Sample No.: KG161290259

Weight: 49.6 lbs.

Hardness:

Via:

Date Rec'd.: 2/8/17

Returned:

SET-UP

Shot Spacing: 3 SHOTS ON 120mm TRIANGLE

Witness Panel: 0.020", 2024-T3 ALUMINUM

Obliquity: 0 deg. Backing Material: NA

Conditioning : AMBIENT

Primary Vel. Screens: 10.0 ft., 20.0 ft.

Primary Vel. Location: 15.0 ft. From Muzzle

Residual Vel. Screens : NA

Residual Vel. Location : NA

Plies/Laminates:

Range to Target: 25.0 ft.

Target to Wit.: 6.0 in.

Range No.: 3

Temp.: 67 F

BP: 29.60 in. Hg

RH: 34%

Barrel No./Gun: R3/.308

Gunner: CHES, BONSALL

Recorder : BONSALL

**AMMUNITION** 

(1): 7.62mm Ball, M80, 149 gr.

(3): (4): Lot No.: UNKNOWN

Lot No.:

Lot No. : Lot No. :

APPLICABLE STANDARDS OR PROCEDURES

(1): STANAG 4569 (ABBREVIATED)

(2): LEVEL: I

(3): REQUIRED VELOCITY: 2666-2798 fps

Shot No.	Ammo.	Time 1 (usec)	Velocity 1 (ft/s)	Time 2 (usec)	Velocity 2 (ft/s)	Avg. Vel. (ft/s)	Vel. Loss (ft/s)	Strike Vel. (ft/s)	Penetration	Footnotes
1 2 3	1 1 1	3644 3662 3671	2744 2731 2724	3648 3665 3675	2741 2729 2721	2743 2730 2723	6 6 6	2737 2724 2717	None None None	
							FOOTNO			

**FOOTNOTES:**